

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



BEHR®
WATER PROOFING
WOOD PROTECTOR
No. 300 NATURAL

RECOMMENDED USES:

Exterior, properly prepared, unsealed wood surfaces such as: Decks, Railings, Shakes, Shingles, Siding, Roofs, Fencing, Planters and Furniture.

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 300 Natural

Tintable Bases/Max Tint

No. 300 – 128 oz.
 Natural – Stock Color*

*Not Tintable

FINISH

N/A

COVERAGE RATE

250-300 sq. ft. (23-28 m.) per gallon.

DRYING TIME

@77°F(25°C) & 50% humidity*
 *Longer dry time is required in cooler temperatures or in higher humidity.

Light Foot Traffic: 24-48 Hours
 Heavy Foot Traffic: 72 Hours

PRIMERS

N/A

COMPOSITION

Vehicle/Active Ingredient:

Alkyd/Acrylic

Percent Solids By Volume:

29.5%

Percent Solids By Weight:

31%

Weight Per Gallon:

8.5 lbs.

VOC

53 gm/l Material (Includes Water)

247 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) www.earth911.org

SURFACE PREPARATION

Test the wood's condition by placing cloth duct tape directly on random areas of the uncoated wood and press firmly. Pull the tape off quickly. If any wood fibers are pulled on to the tape, the wood surface is not sound and you need to follow all of the steps listed for coated wood. If no wood fibers are pulled on to the tape, proceed to step two. Remove algae, fungus, grime, and mildew stains with BEHR® No. 62 Multi-Surface Cleaner & Mildew Stain Remover. Rinse. Follow with BEHR® No. 63 Wood Cleaner Brightener Conditioner to clean, open wood grain, neutralize and rejuvenate the natural color of the wood. Rinse thoroughly.

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .015

Pump Sprayer: High Quality Sprayer with an adjustable tip.

Brush: Nylon/Polyester blend or Pad Applicator

Roller: 3/8" Nap. Roll rough surfaces only.

Thinner: Do Not Thin.

SURFACE PREPARATION

For All Coated Wood: Remove loose wood fibers and/or deteriorated finishes with BEHR® No. 64 15 Minute Quik-Fix™ Deck Finish Remover & Wood Resurfacer. Rinse. Remove algae, fungus, grime, and mildew stains with BEHR® No. 62 Multi-Surface Cleaner & Mildew Stain Remover. Rinse. Follow with BEHR® No. 63 Wood Cleaner Brightener Conditioner to clean, open wood grain, neutralize and rejuvenate the natural color of the wood. Rinse thoroughly.

APPLICATION

The wood surface may be coated when damp/dry. Wipe any standing water off the surface prior to applying the finish. When working with more than one container, intermix to ensure color uniformity. Do Not Thin Product. Stir product before and occasionally during application. Test for penetration and color on a small hidden area before proceeding. If a pump sprayer is used, work in small sections lightly saturating the surface and back-brush/roll immediately to remove excess and evenly distribute the finish. Saturate surface leaving a wet sheen. Maintain a wet edge when applying. Always back-brush during all application methods. Apply product end-to-end or to board lengths to prevent lap marks. Coat wood on all sides for optimum performance. One coat is recommended. Spread rate is approximately 250-300 sq. ft. (23-28 m²) per gallon.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2