

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**PREMIUM SOLID
COLOR DECK,
FENCE & SIDING
STAIN
No. 5010 U. P.W.**

RECOMMENDED USES:

Exterior, properly prepared wood and composite surfaces such as: Decks, Railings, Shakes, Shingles, Siding, Roofs, Fences and Furniture.

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 5010 U.P.W.

Custom colors plus computer color matching available.

Tintable Bases/Max Tint

No. 5010 – 128 oz.

U.P.W. – 2 oz.

FINISH

Flat.

*Sheen Level 7.0 – 10.0 @ 85°

*Substrate Dependant

COVERAGE RATE

250-400 sq. ft. (23-37 m²) per gallon depending on surface texture, porosity and application method
4 mils wet, 1.56 mils dry

DRYING TIME

@75°F & 50% humidity*

*longer dry time required in cooler temperatures and in higher humidity.

Light Foot Traffic: 24 Hours

Recoat: 24-48 Hours

Cured: 72 Hours

PRIMERS

No. 434 Oil-Based Primer

No. 436 Exterior Water-Based Primer

COMPOSITION

Vehicle/Active Ingredient:

Acrylic

Percent Solids By Volume:

40-41%

Percent Solids By Weight:

54-55%

Weight Per Gallon:

10.8-11.0 lbs.

VOC

<78 g/l Coating (excludes water)

<34 Material (Includes water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) www.earth911.org

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .015-.017

Conventional Spray: N/A

Brush: Nylon/Polyester blend or Pad Applicator

Roller: 3/8" Nap.

Thinner: Do Not Thin. If spraying only, thin no more 1/2 pint of water per gallon

SURFACE PREPARATION

For All Uncoated Wood: Test the woods condition by placing cloth duct tape directly on random areas of the uncoated wood and press firmly. Pull the tape off quickly. If any wood fibers are pulled on to the tape, the wood surface is not sound and you need to follow all of the steps listed for coated wood. If no wood fibers are pulled on to the tape, proceed to step two. Remove algae, fungus, grime, and mildew stains with BEHR® No. 62 Multi-Surface Cleaner & Mildew Stain Remover. Rinse. Follow with BEHR® no. 63 wood cleaner brightener conditioner to clean, open wood grain, neutralize and rejuvenate the natural color of the wood. Rinse thoroughly. **For All Coated Wood:** Remove loose wood fibers and/or deteriorated finishes with BEHR® No. 64 15 Minute Quik-Fix™ Deck Finish Remover & Wood Resurfacer. Rinse. Remove algae, fungus, grime, and mildew stains with BEHR® No. 62 Multi-Surface Cleaner & Mildew Stain Remover. Rinse. Follow with BEHR® No. 63 Wood Cleaner Brightener Conditioner to clean, open wood grain, neutralize and rejuvenate the natural color of the wood. Rinse thoroughly.

APPLICATION

Do not use if temperature is below 40°F (4.5°C), above 90°F (32°C), or if rain is expected within 24 hours. Wood surfaces must be completely dry. Prime Redwood, Cedar, Cypress and other bleeding woods with BEHR Exterior Water-Base Acrylic Latex Primer Sealer or BEHR Exterior Oil-Base Primer Sealer to reduce extractive bleeding stains. When working with more than one container of the same color, intermix to ensure color uniformity. Stir stain before and occasionally during application. Maintain a wet edge when applying. Always back-brush and apply product end to end or to board lengths to prevent lap marks. Over-application of stain will lead to surface failure including peeling and cracking. Avoid applying stain too heavily. Do not apply more than two coats. For optimum performance, coat all six sides of wood.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

**To Consult with a Technical Service Representative call
1-800-854-0133 Ext. 2**

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**PREMIUM SOLID
COLOR DECK,
FENCE & SIDING
STAIN
No. 5013 DEEP**

RECOMMENDED USES:

Exterior, properly prepared wood and composite surfaces such as: Decks, Railings, Shakes, Shingles, Siding, Roofs, Fences and Furniture.

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 5013 Deep Base

Custom colors plus computer color matching available.

Tintable Bases/Max Tint

No. 5013 – 116 oz.

Deep Base. – 14 oz.

FINISH

Flat.

*Sheen Level 7.0 – 10.0 @ 85°

*Substrate Dependant

COVERAGE RATE

200-400 sq. ft. (23-37 m²) per gallon depending on surface texture, porosity and application method
5.3 to 6.4 mils wet, 2.0 to 2.5 mils dry

DRYING TIME

@75°F & 50% humidity*

*longer dry time required in cooler temperatures and in higher humidity.

Light Foot Traffic: 24 Hours

Recoat: 24-48 Hours

Cured: 72 Hours

PRIMERS

No. 434 Oil-Based Primer

No. 436 Exterior Water-Based Primer

COMPOSITION

Vehicle/Active Ingredient:

Acrylic

Percent Solids By Volume:

38-39%

Percent Solids By Weight:

48.5-49.5%

Weight Per Gallon:

10.0- 10.2 lbs.

VOC

<70 g/l Coating (excludes water)

<29 g/l Material (includes water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) www.earth911.org

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .015-.017

Conventional Spray: N/A

Brush: Nylon/Polyester blend or Pad Applicator

Roller: 3/8" Nap.

Thinner: Do Not Thin. If spraying only, thin no more 1/2 pint of water per gallon

SURFACE PREPARATION

For All Uncoated Wood: Test the woods condition by placing cloth duct tape directly on random areas of the uncoated wood and press firmly. Pull the tape off quickly. If any wood fibers are pulled on to the tape, the wood surface is not sound and you need to follow all of the steps listed for coated wood. If no wood fibers are pulled on to the tape, proceed to step two. Remove algae, fungus, grime, and mildew stains with BEHR® No. 62 Multi-Surface Cleaner & Mildew Stain Remover. Rinse. Follow with BEHR® no. 63 wood cleaner brightener conditioner to clean, open wood grain, neutralize and rejuvenate the natural color of the wood. Rinse thoroughly. **For All Coated Wood:** Remove loose wood fibers and/or deteriorated finishes with BEHR® No. 64 15 Minute Quik-Fix™ Deck Finish Remover & Wood Resurfacer. Rinse. Remove algae, fungus, grime, and mildew stains with BEHR® No. 62 Multi-Surface Cleaner & Mildew Stain Remover. Rinse. Follow with BEHR® No. 63 Wood Cleaner Brightener Conditioner to clean, open wood grain, neutralize and rejuvenate the natural color of the wood. Rinse thoroughly.

APPLICATION

Do not use if temperature is below 40°F (4.5°C), above 90°F (32°C), or if rain is expected within 24 hours. Wood surfaces must be completely dry. Prime Redwood, Cedar, Cypress and other bleeding woods with BEHR Exterior Water-Base Acrylic Latex Primer Sealer or BEHR Exterior Oil-Base Primer Sealer to reduce extractive bleeding stains. When working with more than one container of the same color, intermix to ensure color uniformity. Stir stain before and occasionally during application. Maintain a wet edge when applying. Always back-brush and apply product end to end or to board lengths to prevent lap marks. Over-application of stain will lead to surface failure including peeling and cracking. Avoid applying stain too heavily. Do not apply more than two coats. For optimum performance, coat all six sides of wood.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

**To Consult with a Technical Service Representative call
1-800-854-0133 Ext. 2**

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**PREMIUM SOLID
COLOR DECK, FENCE
& SIDING STAIN
No. 5016 ACCENT BASE**

RECOMMENDED USES:

Exterior, properly prepared wood and composite surfaces such as: Decks, Railings, Shakes, Shingles, Siding, Roofs, Fences and Furniture.

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 5016 Accent Base

Custom colors plus computer color matching available.

Tintable Bases/Max Tint

No. 5016 – 116 oz.
Accent Base. – 14 oz.

FINISH

Flat. 0

*Sheen Level 7. – 10.0 @ 85°

*Substrate Dependant

COVERAGE RATE

200-400 sq. ft. (23-37 m²) per gallon depending on surface texture, porosity and application method
5.3 to 6.4 mils wet, 2.1 to 2.6 mils dry

DRYING TIME

@75°F & 50% humidity*

*longer dry time required in cooler temperatures and in higher humidity.

Light Foot Traffic: 24 Hours

Recoat: 24-48 Hours

Cured: 72 Hours

PRIMERS

No. 434 Oil-Based Primer

No. 436 Exterior Water-Based Primer

COMPOSITION

Vehicle/Active Ingredient:

Acrylic

Percent Solids By Volume:

40-41%

Percent Solids By Weight:

52-53%

Weight Per Gallon:

10.25-10.55 lbs.

VOC

<66 g/l Coating (excludes water)

<29 g/l Material (includes water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) www.earth911.org

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .015-.017

Conventional Spray: N/A

Brush: Nylon/Polyester blend or Pad Applicator

Roller: 3/8" Nap.

Thinner: Do Not Thin. If spraying only, thin no more 1/2 pint of water per gallon

SURFACE PREPARATION

For All Uncoated Wood: Test the woods condition by placing cloth duct tape directly on random areas of the uncoated wood and press firmly. Pull the tape off quickly. If any wood fibers are pulled on to the tape, the wood surface is not sound and you need to follow all of the steps listed for coated wood. If no wood fibers are pulled on to the tape, proceed to step two. Remove algae, fungus, grime, and mildew stains with BEHR® No. 62 Multi-Surface Cleaner & Mildew Stain Remover. Rinse. Follow with BEHR® no. 63 wood cleaner brightener conditioner to clean, open wood grain, neutralize and rejuvenate the natural color of the wood. Rinse thoroughly. **For All Coated Wood:** Remove loose wood fibers and/or deteriorated finishes with BEHR® No. 64 15 Minute Quik-Fix™ Deck Finish Remover & Wood Resurfacer. Rinse. Remove algae, fungus, grime, and mildew stains with BEHR® No. 62 Multi-Surface Cleaner & Mildew Stain Remover. Rinse. Follow with BEHR® No. 63 Wood Cleaner Brightener Conditioner to clean, open wood grain, neutralize and rejuvenate the natural color of the wood. Rinse thoroughly.

APPLICATION

Do not use if temperature is below 40°F (4.5°C), above 90°F (32°C), or if rain is expected within 24 hours. Wood surfaces must be completely dry. Prime Redwood, Cedar, Cypress and other bleeding woods with BEHR Exterior Water-Base Acrylic Latex Primer Sealer or BEHR Exterior Oil-Base Primer Sealer to reduce extractive bleeding stains. When working with more than one container of the same color, intermix to ensure color uniformity. Stir stain before and occasionally during application. Maintain a wet edge when applying. Always back-brush and apply product end to end or to board lengths to prevent lap marks. Over-application of stain will lead to surface failure including peeling and cracking. Avoid applying stain too heavily. Do not apply more than two coats. For optimum performance, coat all six sides of wood.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

**To Consult with a Technical Service Representative call
1-800-854-0133 Ext. 2**