

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**BEHR® ELASTOMERIC
MASONRY, STUCCO
& BRICK PAINT
NO. 68
WHITE**

RECOMMENDED USES:

Excellent adhesion on new or previously painted exterior vertical surfaces made of stucco, masonry, concrete, concrete block, cement, adjacent or metal trims.

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 68 White

Custom colors plus computer color matching available.

TINT BASE / MAX TINT*

No. 68 – 120 oz.
White – 8 oz.

FINISH

Flat

*Sheen Level 3.5-5.5 @85°

*Substrate Dependant

COVERAGE RATE

75-125 sq. ft. per gallon
10 mils wet, 5 mils dry

DRYING TIME

@77°F & 50% humidity*

*Longer dry time required in cooler temperatures or in higher humidity.

To Touch: 4-6 Hours

Recoat: 24 Hours

Cured: 30 Days

PRIMERS

No. 436 Exterior Water Based Primer

COMPOSITION

Vehicle/Active Ingredient:

100% Acrylic

Percent Solids By Volume:

48%

Percent Solids By Weight:

60%

Weight Per Gallon:

10.8 lbs.

VOC

44gm/l Material (Includes Water)

84 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) www.earth911.org

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .025-.029

Conventional Spray: N/A

Brush: Nylon/Polyester blend

Roller: 1 1/4" Nap.

Thinner: Do Not Thin.

SURFACE PREPARATION

Remove all loose, peeling paint using a scraper or sandpaper. Wash off all chalk, dirt, grease, soap and oil-build-up with mild detergent; remove mildew with BEHR No. 62 Multi-Surface Deck-Prep™ Cleaner & Mildew Stain Remover or bleach and water. Rinse and allow to dry. Cracks and gaps wider than 1/16" should be routed open, dusted, primed and packed with an elastomeric patching compound prior to product application. Scuff sand glossy surfaces before priming. Prime all chalky, glossy or bare surfaces with BEHR Exterior 100% Acrylic Latex Primer & Sealer.

APPLICATION

Use product when surface and air temperature are between 50°- 90°F. Intermix multiple containers to ensure color and sheen uniformity. Apply one coat of about 10 mils wet film thickness. After 24 hours, a second coat of 10 mils wet film thickness must be applied. A third coat may be required to achieve a final dry mil thickness of about 10-15 mils. **Airless Spray:** Tip size and atomization pressure will vary depending upon specific equipment used, the viscosity of the coating and temperatures at the time of application..

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

**To Consult with a Technical Service Representative call
1-800-854-0133 Ext. 2**