

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



BEHR®
INT/EXT
SOLID COLOR
CONCRETE
STAIN No. 800
White Tint Base

RECOMMENDED USES:

Properly prepared Interior or Exterior surfaces such as: Concrete, Masonry Walls, Basements, Patios, Sidewalks, Driveways, Garage Floors*, Pool/Cool Decks**, Tennis Courts, Cement Blocks, Pillars and Brick. Not for use on surfaces subject to hydrostatic pressure.*

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 800 White Tint Base

Tintable Bases/Max Tint

No. 800 – 124 oz.

White Tint Base – 6 oz

Over 1600 custom colors plus computer color matching

FINISH

Flat.

*Sheen Level 5-10 @ 85°

*Substrate Dependant

COVERAGE RATE

400-600 sq. ft. (37-56 m²) per gallon.

DRYING TIME

@77°F & 50% humidity*

*Longer dry time required in cooler temperatures or higher humidity.

Park tires on corrugated cardboard for 14 days after applying stain

Light Foot Traffic: 24 Hours

Recoat: 24 Hours

Heavy Foot Traffic: 72 Hours

Cured: Two Weeks

PRIMERS

No. 880 Bonding Primer

COMPOSITION

Vehicle/Active Ingredient:

100% Acrylic

Percent Solids By Volume:

42%

Percent Solids By Weight:

58%

Weight Per Gallon:

11.8 lbs.

VOC

31gm/l Material (Includes Water)

98 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) www.earth911.org

APPLICATION TOOLS

Airless Spray: Spraying not recommended due to tendency for over application.

Conventional Spray: Spraying not recommended due to tendency for over application.

Brush: Nylon/Polyester blend

Roller: 1/4"-3/8" Nap. Depending on the surface texture.

Thinner: Do Not Thin.

SURFACE PREPARATION

New concrete must cure for a minimum of 30 days. Use over existing coatings may not provide optimal performance. **CLEAN:** Remove dirt, oil and grease stains with BEHR No. 990 Concrete Cleaner & Degreaser. To remove mildew stains, use BEHR No. 62 Multi-Surface Deck-Prep™ Cleaner & Mildew Stain Remover or bleach and water. Follow all label instructions. **ETCH:** For proper penetration and adhesion to new or smooth concrete floors such as garages, use BEHR No. 991 Concrete Etcher & Rust Remover. Follow all label instructions. **PRIME:** Apply BEHR No. 880 Concrete Bonding Primer to increase adhesion of topcoat to uncoated concrete or masonry. Follow all label instructions.

APPLICATION

Intermix all cans of same product to ensure color uniformity. Stir stain before and occasionally during application. Use product when air and surface temperatures are between 50-90°F (10-32°C). Use long, even strokes in one direction to avoid lap lines. Since concrete varies in texture/porosity, two coats may be required for uniform color appearance. Apply a second coat (in a criss-cross direction) if uniformity is needed. Recoat after 24 hours. Periodic touch-ups may be necessary.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



BEHR®
INT/EXT
SOLID COLOR
CONCRETE
STAIN No. 830
DEEP TINT BASE

RECOMMENDED USES:

Properly prepared Interior or Exterior surfaces such as: Concrete, Masonry Walls, Basements, Patios, Sidewalks, Driveways, Garage Floors*, Pool/Cool Decks**, Tennis Courts, Cement Blocks, Pillars and Brick. Not for use on surfaces subject to hydrostatic pressure.*

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 830 Deep Tint Base

Tintable Bases/Max Tint

No. 830 – 116 oz.

Deep Tint Base – 12 oz

Over 1600 custom colors plus computer color matching

FINISH

Flat.

*Sheen Level 5-10 @ 85°

*Substrate Dependant

COVERAGE RATE

400-600 sq. ft. (37-56 m²) per gallon.

DRYING TIME

@77°F & 50% humidity*

*Longer dry time required in cooler temperatures or higher humidity.

Park tires on corrugated cardboard for 14 days after applying stain.

Light Foot Traffic: 24 Hours

Recoat: 24 Hours

Heavy Foot Traffic: 72 Hours

Cured: Two Weeks

PRIMERS

No. 880 Bonding Primer

COMPOSITION

Vehicle/Active Ingredient:

100% Acrylic

Percent Solids By Volume:

40%

Percent Solids By Weight:

52%

Weight Per Gallon:

11.8 lbs.

VOC

35 gm/l Material (Includes Water)

99 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) www.earth911.org

APPLICATION TOOLS

Airless Spray: Spraying not recommended due to tendency for over application.

Conventional Spray: Spraying not recommended due to tendency for over application.

Brush: Nylon/Polyester blend

Roller: 1/4"-3/8" Nap. Depending on the surface texture.

Thinner: Do Not Thin.

SURFACE PREPARATION

New concrete must cure for a minimum of 30 days. Use over existing coatings may not provide optimal performance. **CLEAN:** Remove dirt, oil and grease stains with BEHR No. 990 Concrete Cleaner & Degreaser. To remove mildew stains, use BEHR No. 62 Multi-Surface Deck-Prep™ Cleaner & Mildew Stain Remover or bleach and water. Follow all label instructions. **ETCH:** For proper penetration and adhesion to new or smooth concrete floors such as garages, use BEHR No. 991 Concrete Etcher & Rust Remover. Follow all label instructions. **PRIME:** Apply BEHR No. 880 Concrete Bonding Primer to increase adhesion of topcoat to uncoated concrete or masonry. Follow all label instructions.

APPLICATION

Intermix all cans of same product to ensure color uniformity. Stir stain before and occasionally during application. Use product when air and surface temperatures are between 50-90°F (10-32°C). Use long, even strokes in one direction to avoid lap lines. Since concrete varies in texture/porosity, two coats may be required for uniform color appearance. Apply a second coat (in a criss-cross direction) if uniformity is needed. Recoat after 24 hours. Periodic touch-ups may be necessary.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2