

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**BEHR® INT/EXT
SEMI-TRANSPARENT
CONCRETE STAIN
No. 850
Tint Base**

RECOMMENDED USES:

For uncoated and unsealed, properly prepared Interior or Exterior Patios, Pavers, Driveways, Walkways*, Garage Floors*, Pool or Cool Decks** and other concrete floors.*

AVAILABLE IN: Gallon Only

COLORS

No. 850 Tint Base

TINT BASE/MAX TINT

No. 850 – 126 oz.
Tint Base – 4 oz

FINISH

Flat.

COVERAGE RATE

175-250 sq. ft. (16-23 m²) per gallon depending on the porosity and texture of the surface. Apply second coat at a spread rate of 250-350 sq. ft. (23-32 m²) per gallon.

DRYING TIME

@77°F & 50% humidity*

*Longer dry time required in cooler temperatures or higher humidity.

Park tires on corrugated cardboard for 7 days after applying stain

Recoat: 4 Hours
Light Foot Traffic: 24 Hours
Heavy Foot Traffic: 72 Hours
Full Cure: 30 Days

PRIMERS

No. 880 Bonding Primer

COMPOSITION

Vehicle/Active Ingredient:

100% Acrylic

Percent Solids By Volume:

17%

Percent Solids By Weight:

19%

Weight Per Gallon:

8.5 lbs.

VOC

59 gm/l Material (Includes Water)

249 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) www.earth911.org

Optional Topcoat

For added protection, use BEHR No. 985 Wet-Look Sealer for a high gloss wet-look finish or BEHR No. 910 Clear 1-Part Epoxy Concrete & Garage Floor Paint for a semi-gloss finish. Allow stain at least 4 hours to dry before topcoating. Follow all label instructions.

APPLICATION TOOLS

Airless Spray: N/A.

Conventional Spray: N/A

Pump Sprayer: High Quality with Adjustable tip.

Brush: N/A

Roller: 3/8" Nap. To Back Roll

Thinner: Do Not Thin.

SURFACE PREPARATION

New concrete must cure for a minimum of 30 days. Use over existing coatings may not provide optimal performance. **CLEAN:** Remove dirt, oil and grease stains with BEHR No. 990 Concrete Cleaner & Degreaser. To remove mildew stains, use BEHR No. 62 Multi-Surface Deck-Prep™ Cleaner & Mildew Stain Remover or bleach and water. Follow all label instructions. **ETCH:** For proper penetration and adhesion to new or smooth concrete floors such as garages, use BEHR No. 991 Concrete Etcher & Rust Remover. Follow all label instructions. **PRIME:** Apply BEHR No. 880 Concrete Bonding Primer to increase adhesion of topcoat to uncoated concrete or masonry. Follow all label instructions.

APPLICATION

Intermix cans of same products to ensure color uniformity. **STIR** thoroughly before and during application. Use product when temperature is between 50–90°F (10–32°C). Apply stain in small concrete sections approximately 4' by 4' (1.2 m x 1.2 m). Work quickly and feather edges. Apply at a fine spray setting using a circular motion. Immediately after spraying, **back-roll** with a 3/8" nap roller or pad applicator to achieve a more even appearance. Allow first coat to dry for 4 hours before deciding if a second coat is necessary. An additional coat will provide a darker and more uniform color. **NOTE:** Horizontal surfaces may be subject to premature wear. Periodic touch-ups may be necessary.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

**To Consult with a Technical Service Representative call
1-800-854-0133 Ext. 2**