

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or [www.behr.com](http://www.behr.com)



**BEHR®**  
**Basement & Masonry**  
**Waterproofing Paint**  
**No. 875**

### RECOMMENDED USES:

*Walls subject to hydrostatic pressure. Ideal for above or below grade basement walls, retaining walls, masonry walls, cinder blocks, stucco, brick, foundations and landscape walls.*

### AVAILABLE IN: Gallon & Five Gallon

#### COLORS

No. 875 White

#### Tintable Bases/Max Tint

No. 875 White – 126 oz  
White Base - 4oz

#### FINISH

Flat.

\*Gloss Level <5% @ 60°

\*Substrate Dependant

#### COVERAGE RATE

On rough porous masonry, 75–100 sq. ft. (7-9m<sup>2</sup>) per gallon. On smoother surfaces, 100–125 sq. ft. (9-12m<sup>2</sup>) per gallon. 13 mils wet, 6 mils dry

#### DRYING TIME

@77°F(25°C) and 50% humidity\*

\*Longer dry time required in cooler temperatures and in higher humidity.

To Touch: 1 Hours

Recoat: 4 Hours

Full Cure: 7-14 Days

#### PRIMERS

N/A

#### COMPOSITION

**Vehicle/Active Ingredient:**

Acrylic

**Percent Solids By Volume:**

44%

**Percent Solids By Weight:**

60%

**Weight Per Gallon:**

11.7 lbs.

#### VOC

123 g/l Material (includes water)

219 g/l Coatings (includes water)

#### Flashpoint

N/A

#### MSDS

Available @ [www.behr.com](http://www.behr.com)

Or 1-800-854-0133 Ext. 2

#### Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) [www.earth911.org](http://www.earth911.org)

#### APPLICATION TOOLS

**Airless Spray:** **Filter:** Remove **Tip:** .023-.025

**Fluid pressure:** 2,200-3,200 psi

**Conventional Spray:** N/A

**Brush:** Nylon/Polyester Blend

**Roller:** 3/8" to 3/4" Nap. Depending on the surface texture.

**Thinner:** Do Not Thin.

#### SURFACE PREPARATION

All surfaces must be clean and free of dirt, dust, efflorescence, oil and previous coatings. Clean surface with BEHR® No. 990 Concrete Cleaner & Degreaser. All holes or cracks must be properly patched with a fast setting hydraulic cement. Eliminate mildew stains with BEHR No. 62 Multi-Surface Deck-Prep Cleaner & Mildew Stain Remover or bleach and water. Remove efflorescence with BEHR No. 991 Concrete Etcher & Rust Remover. For Exterior application; use BEHR No. 64 15 Minute Quik-Fix™ Deck Finish Remover & Wood Resurfacer to remove latex or oil-base finishes. For Interior application; use a chemical stripper designed for interior use. New concrete must be completely cured (minimum 30 days) before application.

#### APPLICATION

Stir well before use. Do not thin product. **Use with adequate ventilation.** Use product when the surface and air temperature are between 50°–90°F (10°–32°C). Apply to dry or lightly damp masonry walls. Two coats minimum are required: **First Coat:** Using a brush, work the waterproofer into the pores of the masonry. **Second Coat:** Using a brush, roller or sprayer, cover the entire surface. Properly fill any voids left after first coat. Additional spot application may be needed depending on the porosity of the surface. **Important: If leaking is still present after two coats, it indicates that voids or pinholes are still open. Reapply product to these areas. Do not under apply.**

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

**To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2**

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or [www.behr.com](http://www.behr.com)



**BEHR®**  
**Basement & Masonry**  
**Waterproofing Paint**  
**No. 2-875**

### RECOMMENDED USES:

*Walls subject to hydrostatic pressure. Ideal for above or below grade basement walls, retaining walls, masonry walls, cinder blocks, stucco, brick, foundations and landscape walls.*

### AVAILABLE IN: Gallon & Five Gallon

#### COLORS

No. 2-875 White

#### Tintable Bases/Max Tint

No. 2-875 White – 126 oz  
White Base - 4oz

#### FINISH

Flat.

\*Gloss Level <5% @ 60°  
\*Substrate Dependant

#### COVERAGE RATE

On rough porous masonry, 75–100 sq. ft. (7-9m<sup>2</sup>) per gallon. On smoother surfaces, 100–125 sq. ft. (9-12m<sup>2</sup>) per gallon. 13 mils wet, 6 mils dry

#### DRYING TIME

@77°F(25°C) and 50% humidity\*  
\*Longer dry time required in cooler temperatures and in higher humidity.

To Touch: 1 Hours  
Recoat: 4 Hours  
Full Cure: 7-14 Days

#### PRIMERS

N/A

#### COMPOSITION

**Vehicle/Active Ingredient:**

Acrylic

**Percent Solids By Volume:**

44%

**Percent Solids By Weight:**

60%

**Weight Per Gallon:**

11.7 lbs.

#### VOC

48 g/l Material (includes water)  
97 g/l Coating (excludes water)

#### Flashpoint

N/A

#### MSDS

Available @ [www.behr.com](http://www.behr.com)  
Or 1-800-854-0133 Ext. 2

#### Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) [www.earth911.org](http://www.earth911.org)

#### APPLICATION TOOLS

**Airless Spray:** **Filter:** Remove **Tip:** .023-.025  
**Fluid pressure:** 2,200-3,200 psi

**Conventional Spray:** N/A

**Brush:** Nylon/Polyester Blend

**Roller:** 1/2" to 3/4" Nap. Depending on the surface texture.

**Thinner:** Do Not Thin.

#### SURFACE PREPARATION

All surfaces must be clean and free of dirt, dust, efflorescence, oil and previous coatings. Clean surface with BEHR® No. 990 Concrete Cleaner & Degreaser. All holes or cracks must be properly patched with a fast setting hydraulic cement. Eliminate mildew stains with BEHR No. 62 Multi-Surface Deck-Prep Cleaner & Mildew Stain Remover or bleach and water. Remove efflorescence with BEHR No. 991 Concrete Etcher & Rust Remover. For Exterior application; use BEHR No. 64 15 Minute Quik-Fix™ Deck Finish Remover & Wood Resurfacer to remove latex or oil-base finishes. For Interior application; use a chemical stripper designed for interior use. New concrete must be completely cured (minimum 30 days) before application.

#### APPLICATION

Stir well before use. Do not thin product. **Use with adequate ventilation.** Use product when the surface and air temperature are between 50°–90°F (10°–32°C). Apply to dry or lightly damp masonry walls. Two coats minimum are required: **First Coat:** Using a brush, work the waterproofer into the pores of the masonry. **Second Coat:** Using a brush, roller or sprayer, cover the entire surface. Properly fill any voids left after first coat. Additional spot application may be needed depending on the porosity of the surface. **Important: If leaking is still present after two coats, it indicates that voids or pinholes are still open. Reapply product to these areas. Do not under apply.**

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

**To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2**