

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**BEHR® INT/EXT
CONCRETE
BONDING
PRIMER
No. 880**

RECOMMENDED USES: Use on Interior or Exterior surfaces such as: Concrete, Masonry, Stucco, Cinder Block and any Porous Stone or Brick. Not designed for use on wood, metal or silicone treated surfaces. Do not use on coated surfaces. Use only on porous surfaces. **Note:** Some Surfaces May Appear Slightly Darker After Product Dries.

AVAILABLE IN: Gallon Only

COLORS

No. 880 Milky and dries clear

Tintable Bases/Max Tint

No. 880 – 128 oz.

Not Tintable

FINISH

Gloss

Sheen Level 15-20 @ 60°

COVERAGE RATE

350-400 sq. ft. (33-37 m²) per gallon depending on texture and porosity.

DRYING TIME

@77°F & 50% humidity. Must apply a topcoat after at least 8 hours, but before 30 days.

To Touch: 2-4 Hours

Recoat: 8 Hours

PRIMERS

N/A

COMPOSITION

Vehicle/Active Ingredient:

Epoxy

Percent Solids By Volume:

16%

Percent Solids By Weight:

15%

Weight Per Gallon:

8.6 lbs.

VOC

37 gm/l Material (Includes Water)

187 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Commercial Brush Cleaner.

Recycle or dispose of paint call 1-

800-CLEANUP (U.S.A. only)

www.earth911.org

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: 015-.017

Conventional Spray: Not Recommended

Brush: Nylon/Polyester blend or Pad Applicator

Roller: 3/8"-1/2" Nap. Depending on the surface texture.

Thinner: Do Not Thin.

SURFACE PREPARATION

New concrete must cure for a minimum of 30 days prior to priming. Patch all holes and cracks and allow to dry. For touch-ups where surface coatings have failed, completely remove any loose or peeling paint. Do not apply over previously coated surfaces. Remove all dirt, grease and oil with BEHR® No. 990 Concrete Cleaner & Degreaser. Refer to product label for specific instructions. Etch dense, smooth concrete using BEHR No. 991 Concrete Etcher & Rust Remover. Refer to product label for specific instructions.

APPLICATION

DO NOT THIN. Stir paint before and occasionally during application. Use product when air and surface temperatures are between 50-90°F (10-32°C). Initial foaming will disappear upon drying.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2