

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**BEHR® INT/EXT
1-PART EPOXY
ACRYLIC GARAGE
FLOOR PAINT
No. 900 WHITE TINT**

RECOMMENDED USES:

*Interior or Exterior surfaces such as: Porous Concrete, Masonry, Stone and Brick. Ideal for horizontal surfaces such as: Garage Floors, Driveways, Basements, Porches and Pool/Cool Decks. **Do not** use on vertical surfaces or areas subject to hydrostatic pressure. **NOT** for industrial use. **DO NOT** use on areas subject to fork-lifts.*

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 900 White

Tintable Bases/Max Tint

No. 900 – 122 oz.

White - 6oz

Over 1600 custom colors plus computer color matching

FINISH

Satin

* Gloss Level 12-22 @ 60°

*Substrate Dependant

COVERAGE RATE

400-500 sq. ft. (37-46 m²) per gallon on smooth surfaces and 300-400 sq. ft. (28-37 m²) per gallon on rough surfaces.
3.2 mils wet, 1.0 mils dry

DRYING TIME

@77°F (25°C) and 50% humidity*

*Longer dry time required in cooler temperatures and in higher humidity.

To Touch: 2 Hours

Recoat: 24 Hours

Repositioning of Furniture: 72 Hours

Park on: 7 days

Full Cure: 30 Days

PRIMERS

No. 880 Concrete Bonding Primer

COMPOSITION

Vehicle/Active Ingredient:

Styrene Acrylic

Percent Solids By Volume:

29.9%

Percent Solids By Weight:

39.9%

Weight Per Gallon:

9.7 lbs.

VOC

98 gm/l Material (Includes Water)

242 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Use soap and water. Properly dispose of all soiled rags and protect unused product from freezing. To recycle or properly dispose of paint in your community call 1-800-CLEANUP or visit www.Earth911.org.

CAUTION: Painted surfaces may become slippery when wet. Adding BEHR® No. 970 Non-Skid Floor Finish Additive will help prevent slip. Follow all label instructions.

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .015-.017

Conventional Spray: See manufacturer recommendations

Brush: Nylon/Polyester blend or Pad Applicator

Roller: 3/8" Nap. Depending on the surface texture.

Thinner: Do Not Thin.

SURFACE PREPARATION

New and Uncoated Concrete or Masonry Surfaces: New concrete must cure for a minimum of 30 days. For proper penetration and adhesion of topcoat, use BEHR® No. 991 Concrete & Masonry Cleaner/Etcher to clean and etch the surface. Follow all label instructions. Apply BEHR No. 880 Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions

Painted, Stained or Sealed Concrete: Option 1- To completely strip the entire surface, use BEHR No. 992 Concrete & Masonry Paint Stripper. Follow all label instructions. **Option 2-** To recoat over an existing coating, remove any loose or peeling paint and scuff sand the surface. Use BEHR No. 990 Concrete & Masonry Cleaner/Degreaser to clean previously coated surfaces in sound condition. Use BEHR No. 991 Concrete & Masonry Cleaner/Etcher to clean and etch any bare concrete area. Follow all label instructions. Spot prime all bare concrete areas with BEHR No. 880 Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions.

APPLICATION

DO NOT THIN. Intermix all cans of same product to ensure color uniformity. Stir before applying. Use product when air and surface temperatures are between 50-90°F (10-32°C). Allow first coat to dry 24 hours before deciding if a second coat is necessary. For uniformity apply a second coat (in a criss-cross direction). Do Not Apply More Than Two Coats. An annual touch-up may be required in areas subject to tire traffic.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**BEHR® INT/EXT
1-PART EPOXY
ACRYLIC GARAGE
FLOOR PAINT
No. 901 SILVER GRAY**

RECOMMENDED USES:

Interior or Exterior surfaces such as: Porous Concrete, Masonry, Stone and Brick. Ideal for horizontal surfaces such as: Garage Floors, Driveways, Basements, Porches and Pool/Cool Decks. **Do not** use on vertical surfaces or areas subject to hydrostatic pressure. **NOT** for industrial use. **DO NOT** use on areas subject to fork-lifts.

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 901 Silver Gray

Tintable Bases/Max Tint

No. 901 – 128 oz.

Silver Gray – Stock Color*

*May not be available in all markets.

FINISH

Satin

* Sheen Level 15-25 @ 60°

*Substrate Dependant

COVERAGE RATE

400-500 sq. ft. (37-46 m²) per gallon on smooth surfaces and 300-400 sq. ft. (28-37 m²) per gallon on rough surfaces.
3.2 mils wet, 1.0 mils dry

DRYING TIME

@77°F (25°C) and 50% humidity*
*Longer dry time required in cooler temperatures and in higher humidity.

To Touch: 2 Hours

Recoat: 24 Hours

Repositioning of Furniture: 72 Hours

Park on: 7 days

Full Cure: 30 Days

PRIMERS

No. 880 Concrete Bonding Primer

COMPOSITION

Vehicle/Active Ingredient:

Styrene Acrylic

Percent Solids By Volume:

31.0%

Percent Solids By Weight:

40.1%

Weight Per Gallon:

9.6 lbs.

VOC

97 gm/l Material (Includes Water)

236 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Use soap and water. Properly dispose of all soiled rags and protect unused product from freezing. To recycle or properly dispose of paint in your community call 1-800-CLEANUP or visit www.Earth911.org.

CAUTION: Painted surfaces may become slippery when wet. Adding BEHR® No. 970 Non-Skid Floor Finish Additive will help prevent slip. Follow all label instructions.

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .015-.017

Conventional Spray: See manufacturer recommendations

Brush: Nylon/Polyester blend or Pad Applicator

Roller: 3/8" Nap. Depending on the surface texture.

Thinner: Do Not Thin.

SURFACE PREPARATION

New and Uncoated Concrete or Masonry Surfaces: New concrete must cure for a minimum of 30 days. For proper penetration and adhesion of topcoat, use BEHR® No. 991 Concrete & Masonry Cleaner/Etcher to clean and etch the surface. Follow all label instructions

Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions
Painted, Stained or Sealed Concrete: Option 1- To completely strip the entire surface, use BEHR No. 992 Concrete & Masonry Paint Stripper. Follow all label instructions. **Option 2-** To recoat over an existing coating, remove any loose or peeling paint and scuff sand the surface. Use BEHR No. 990 Concrete & Masonry Cleaner/Degreaser to clean previously coated surfaces in sound condition. Use BEHR No. 991 Concrete & Masonry Cleaner/Etcher to clean and etch any bare concrete area. Follow all label instructions. Spot prime all bare concrete areas with BEHR No. 880 Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions.

APPLICATION

DO NOT THIN. Intermix all cans of same product to ensure color uniformity. Stir before applying. Use product when air and surface temperatures are between 50-90°F (10-32°C). Allow first coat to dry 24 hours before deciding if a second coat is necessary. For uniformity apply a second coat (in a criss-cross direction). Do Not Apply More Than Two Coats. An annual touch-up may be required in areas subject to tire traffic.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

**To Consult with a Technical Service Representative call
1-800-854-0133 Ext. 2**

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**BEHR® INT/EXT
1-PART EPOXY
ACRYLIC GARAGE
FLOOR PAINT
No. 902 SLATE GRAY**

RECOMMENDED USES:

Interior or Exterior surfaces such as: Porous Concrete, Masonry, Stone and Brick. Ideal for horizontal surfaces such as: Garage Floors, Driveways, Basements, Porches and Pool/Cool Decks. **Do not** use on vertical surfaces or areas subject to hydrostatic pressure. **NOT** for industrial use. **DO NOT** use on areas subject to fork-lifts.

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 902 Slate Gray

Tintable Bases/Max Tint

No. 902 – 128 oz.
Slate Gray – Stock Color*

*May not be available in all markets.

FINISH

Satin
* Sheen Level 15-25 @ 60°
*Substrate Dependant

COVERAGE RATE

400-500 sq. ft. (37-46 m²) per gallon on smooth surfaces and 300-400 sq. ft. (28-37 m²) per gallon on rough surfaces.
3.2 mils wet, 1.0 mils dry

DRYING TIME

@77°F (25°C) and 50% humidity*
*Longer dry time required in cooler temperatures and in higher humidity.

To Touch: 2 Hours
Recoat: 24 Hours
Repositioning of Furniture: 72 Hours
Park on: 7 days
Full Cure: 30 Days

PRIMERS

No. 880 Concrete Bonding Primer

COMPOSITION

Vehicle/Active Ingredient:
Styrene Acrylic
Percent Solids By Volume:
31.3%
Percent Solids By Weight:
39.7%
Weight Per Gallon:
9.5 lbs.

VOC

99 gm/l Material (Includes Water)
237 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com
Or 1-800-854-0133 Ext. 2

Clean Up

Use soap and water. Properly dispose of all soiled rags and protect unused product from freezing. To recycle or properly dispose of paint in your community call 1-800-CLEANUP or visit www.Earth911.org.

CAUTION: Painted surfaces may become slippery when wet. Adding BEHR® No. 970 Non-Skid Floor Finish Additive will help prevent slip. Follow all label instructions.

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .015-.017

Conventional Spray: See manufacturer recommendations

Brush: Nylon/Polyester blend or Pad Applicator

Roller: 3/8" Nap. Depending on the surface texture.

Thinner: Do Not Thin.

SURFACE PREPARATION

New and Uncoated Concrete or Masonry Surfaces: New concrete must cure for a minimum of 30 days. For proper penetration and adhesion of topcoat, use BEHR® No. 991 Concrete & Masonry Cleaner/Etcher to clean and etch the surface. Follow all label instructions. Use BEHR No. 992 Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions.
Painted, Stained or Sealed Concrete: Option 1- To completely strip the entire surface, use BEHR No. 992 Concrete & Masonry Paint Stripper. Follow all label instructions. **Option 2-** To recoat over an existing coating, remove any loose or peeling paint and scuff sand the surface. Use BEHR No. 990 Concrete & Masonry Cleaner/Degreaser to clean previously coated surfaces in sound condition. Use BEHR No. 991 Concrete & Masonry Cleaner/Etcher to clean and etch any bare concrete area. Follow all label instructions. Spot prime all bare concrete areas with BEHR No. 880 Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions.

APPLICATION

DO NOT THIN. Intermix all cans of same product to ensure color uniformity. Stir before applying. Use product when air and surface temperatures are between 50-90°F (10-32°C). Allow first coat to dry 24 hours before deciding if a second coat is necessary. For uniformity apply a second coat (in a criss-cross direction). Do Not Apply More Than Two Coats. An annual touch-up may be required in areas subject to tire traffic.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**BEHR® INT/EXT
1-PART EPOXY
No. 910
Clear Semi-Gloss**

RECOMMENDED USES:

Interior or Exterior surfaces such as: Porous Concrete, Masonry, Stone and Brick. Ideal for horizontal surfaces such as: Garage Floors, Driveways, Basements, Porches and Pool/Cool Decks. **Do not** use on vertical surfaces or areas subject to hydrostatic pressure. **NOT** for industrial use. **DO NOT** use on areas subject to fork-lifts.

AVAILABLE IN: Gallon only

COLORS

No. 910 Clear Semi-Gloss

Tintable Bases/Max Tint

No. 910 – 128 oz.
Clear /Semi-Gloss – Stock Color*

*May not be available in all markets.

FINISH

Semi-Gloss
Gloss Level 45-55 @ 60°

COVERAGE RATE

400-500 sq. ft. (37-46 m²) per gallon on smooth surfaces and 300-400 sq. ft. (28-37 m²) per gallon on rough surfaces. 4 mils wet, 1.70 mils dry

DRYING TIME

@77°F (25°C) and 50% humidity*
*Longer dry time required in cooler temperatures and in higher humidity.

To Touch: 2 Hours
Recoat: 24 Hours
Repositioning of Furniture: 72 Hours
Park on: 7 days before parking on.
Full Cure: 30 Days

PRIMERS

No. 880 Concrete Bonding Primer

COMPOSITION

Vehicle/Active Ingredient:
100% Acrylic
Percent Solids By Volume:
32%
Percent Solids By Weight:
34%
Weight Per Gallon:
8.5 lbs.

VOC

76 gm/l Material (Includes Water)
189 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com
Or 1-800-854-0133 Ext. 2

Clean Up

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) www.earth911.org

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .015-.017

Conventional Spray: See manufacturer recommendations

Brush: Nylon/Polyester blend

Roller: 3/8"-1/2" Nap. Depending on the surface texture.

Thinner: Do Not Thin. If spraying only, thin no more 1/2 pint of water per gallon

SURFACE PREPARATION

New And Uncoated Concrete or Masonry Surfaces: New concrete must cure for a minimum of 30 days. **CLEAN:** Remove dirt, oil and grease stains with BEHR No. 990 Concrete Cleaner & Degreaser. Follow all label instructions. **ETCH:** For proper penetration and adhesion of topcoat, use BEHR No. 991 Concrete Etcher & Rust Remover. Follow all label instructions. **PRIME:** Apply BEHR No. 880 Concrete Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions.

Painted, Stained or Sealed Concrete: Remove any loose or peeling paint and scuff sand the surface. **CLEAN:** Remove dirt, oil and grease stains with BEHR No. 990 Concrete Cleaner & Degreaser. Follow all label instructions. **ETCH:** Spot etch all exposed concrete with BEHR No. 991 Concrete Etcher & Rust Remover. Follow all label instructions. **PRIME:** Spot prime all exposed areas with BEHR No. 880 Concrete Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions.

APPLICATION

Use product when air and surface temperatures are between 50-90°F (10-32°C). Intermix all cans of same product to ensure color uniformity. Stir before applying. If a second coat is necessary. For uniformity apply a second coat (in a criss-cross direction). **Do Not Apply More Than Two Coats.** An annual touch-up may be required in areas subject to tire traffic.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or www.behr.com



**BEHR® INT/EXT
1-PART EPOXY
ACRYLIC GARAGE
FLOOR PAINT
No. 930 DEEP BASE**

RECOMMENDED USES:

Interior or Exterior surfaces such as: Porous Concrete, Masonry, Stone and Brick. Ideal for horizontal surfaces such as: Garage Floors, Driveways, Basements, Porches and Pool/Cool Decks. **Do not** use on vertical surfaces or areas subject to hydrostatic pressure. **NOT** for industrial use. **DO NOT** use on areas subject to fork-lifts.

AVAILABLE IN: Gallon & Five Gallon

COLORS

No. 930 Deep Base

Tintable Bases/Max Tint

No. 930 – 116 oz.

Deep Base - 12oz

Over 1600 custom colors plus computer color matching

FINISH

Satin

* Sheen Level 15-25 @ 60°

*Substrate Dependant

COVERAGE RATE

400-500 sq. ft. (37-46 m2) per gallon on smooth surfaces and 300-400 sq. ft. (28-37 m2) per gallon on rough surfaces.

3.2 mils wet, 1.0 mils dry

DRYING TIME

@77°F (25°C) and 50% humidity*

*Longer dry time required in cooler temperatures and in higher humidity.

To Touch: 2 Hours

Recoat: 24 Hours

Repositioning of Furniture: 72 Hours

Park on: 7 days

Full Cure: 30 Days

PRIMERS

No. 880 Concrete Bonding Primer

COMPOSITION

Vehicle/Active Ingredient:

Styrene Acrylic

Percent Solids By Volume:

30.1%

Percent Solids By Weight:

35.5%

Weight Per Gallon:

9.0 lbs.

VOC

99 gm/l Material (Includes Water)

245 gm/l Coating (Excludes Water)

Flashpoint

N/A

MSDS

Available @ www.behr.com

Or 1-800-854-0133 Ext. 2

Clean Up

Use soap and water. Properly dispose of all soiled rags and protect unused product from freezing. To recycle or properly dispose of paint in your community call 1-800-CLEANUP or visit www.Earth911.org.

CAUTION: Painted surfaces may become slippery when wet. Adding BEHR® No. 970 Non-Skid Floor Finish Additive will help prevent slip. Follow all label instructions.

APPLICATION TOOLS

Airless Spray: Filter: 60 mesh Tip: .015-.017

Conventional Spray: See manufacturer recommendations

Brush: Nylon/Polyester blend or Pad Applicator

Roller: 3/8" Nap. Depending on the surface texture.

Thinner: Do Not Thin.

SURFACE PREPARATION

New and Uncoated Concrete or Masonry Surfaces: New concrete must cure for a minimum of 30 days. For proper penetration and adhesion of topcoat, use BEHR® No. 991 Concrete & Masonry Cleaner/Etcher to clean and etch the surface. Follow all label instructions. Apply BEHR No. 992 Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions

Painted, Stained or Sealed Concrete: Option 1- To completely strip the entire surface, use BEHR No. 992 Concrete & Masonry Paint Stripper. Follow all label instructions. **Option 2-** To recoat over an existing coating, remove any loose or peeling paint and scuff sand the surface. Use BEHR No. 990 Concrete & Masonry Cleaner/Degreaser to clean previously coated surfaces in sound condition. Use BEHR No. 991 Concrete & Masonry Cleaner/Etcher to clean and etch any bare concrete area. Follow all label instructions. Spot prime all bare concrete areas with BEHR No. 880 Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface. Follow all label instructions.

APPLICATION

DO NOT THIN. Intermix all cans of same product to ensure color uniformity. Stir before applying. Use product when air and surface temperatures are between 50-90°F (10-32°C). Allow first coat to dry 24 hours before deciding if a second coat is necessary. For uniformity apply a second coat (in a criss-cross direction). Do Not Apply More Than Two Coats. An annual touch-up may be required in areas subject to tire traffic.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2