



PREMIUM 2-PART EPOXY GARAGE FLOOR COATING GRAY & TAN KIT

NO. 950 & NO. 955



PRODUCT INFORMATION

BEHR® PREMIUM 2-PART EPOXY GARAGE FLOOR COATING is a decorative high-performance, water-based concrete floor coating. It provides long-lasting protection against motor oil, gasoline, antifreeze, brake fluid, salt, and hot tire pick-up. This durable semi-gloss finish is easy-to-clean and also resists scuffing, fading, cracking, peeling and blistering. It requires no priming and once mixed, is ready for use, allowing up to 8 hours of working time (pot life). BEHR® PREMIUM 2-PART EPOXY GARAGE FLOOR COATING is formulated to withstand the harsh elements common to most garage floors, new & old, while maintaining an easy-to-clean, showroom quality appearance.

RECOMMENDED USES:

Interior garage floors protected from the sun and other concrete surfaces. DO NOT use over surfaces subject to hydrostatic pressure, surfaces treated with sealers, loose or peeling previously painted surfaces or loose or damage concrete.

PRODUCT SPECIFICATIONS:

Tint Bases/Max Tint:

- Behr Premium 2 Part Epoxy Garage Floor Coating
- Quart Activator – Silver Gray No. 960 30 fl oz
- Quart Activator – Tan No. 961 30 fl oz
- Base – 92 fl oz. (maximum tint 6fl. Oz.)

Finish:

Semi-gloss level 65-75 @ 60° gloss meter

Sheen:

- 15-25 @ 60°
- 40-60 @ 85°

Vehicle/Active Ingredient:

Epoxy/Amine

*Weight Per Gallon: 9.56-9.96

***% Solids:**

- By Volume: 34-36%
- By Weight: 43-45%

VOC: <50 (g/l) (when mixed)

Flash Point: Not Applicable

***Recommended Film Thickness:**

- Wet: 8 mils / Dry: 2.8 mils @ 200 sq ft
- Wet: 6.4 mils / Dry: 2.2 mils @ 250 sq ft

***Coverage Rate:** Apply an even coat using a 3/8" (10 mm) nap roller cover (included in kit) at a spread rate not to exceed 200-250 sq. ft. per gallon (19-24 m² per 3.79 L).

MIXING

Pour PART A into PART B and stir thoroughly for at least 5 minutes or until you achieve a uniform color. Product is ready to use after mixing. Do not leave container in direct sunlight and keep lid on product when not in use. This product must be used within 8 hours of initial mixing (pot life).

APPLICATION:

Do Not Thin Product. Use product when air and surface temperatures are between 50-95°F. While only one coat is recommended for most applications, a second coat may be applied for increased sheen and optimum performance (apply second coat in the opposite direction from the first coat). Optional: If planning to use the colored flakes, apply BEHR® Premium 2-Part Epoxy Garage Floor Coating in 3' x 3' (1 x 1 m) sections. Immediately toss the color flakes directly onto the wet painted surface. Refer to product label for application instructions.

For Previously Coated Concrete (Oil or Water Base Finishes)

Previously painted concrete may be repainted only if it has excellent adhesion to the floor. Remove any loose or peeling paint by sanding (medium grit paper) or wire brushing the surface. To completely remove all existing coating, use BEHR® Concrete & Masonry Paint Stripper No. 992. Dull glossy surfaces by scuff-sanding or using a chemical deglosser. The surface must be clean, dry and free of dust, dirt, grease, oil or other contaminants. Use BEHR® No. K-109924 CONCRETE CLEANER & ETCHER to clean the surface. Follow all label instructions. Rinse surface thoroughly using a garden hose with the nozzle set in a stream pattern. Allow the surface to dry completely. Excess residue may interfere with the adhesion of the BEHR® PREMIUM 2-PART EPOXY GARAGE FLOOR COATING. Wipe your fingers over the clean floor to check for dust or powder. If residue is visible on your fingers, repeat the rinsing step. Remove excess water with a squeegee or mop. Remove any remaining oil or grease spots on your concrete using BEHR® Concrete & Masonry Degreaser & Cleaner No. 990. Follow all label instructions. Note: The floor must be thoroughly cleaned, completely rinsed and dry for the coating to adhere properly to the surface.

COMPLIES WITH THE BELOW AS OF 3/22/2011			
OTC	YES	CARB	YES
SCAQMD	YES		

APPLICATION TOOLS:

- Brush:** Nylon/Polyester blend
- Roller:** 3/8" nap roller cover.
- Thinner:** Do Not Thin.

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- For best results, apply at temperatures between 50°F - 90°F. Temperatures above 90°F may affect the application such as drying to fast. Avoid painting in direct sun. NOTE: If the surface is hot to the touch it should be considered to hot to apply this coating.
- Avoid heavy traffic for 72 hours.
- Shelf life under normal conditions is two years unopened.

DRY TIME:

- Dries to touch in two hours at 77°F and 50% humidity.
- The floor may be subjected to light foot traffic after 6-8 hours.
- Allow 24 hours before subjecting surface to heavy foot traffic or repositioning furniture.
- Allow at least 3 days drying before subjecting painted surface to automobile tires. Additional dry time is needed in cooler temperatures and higher humidity.
- Premature heavy traffic will cause coating failure, which may require spot recoating.
- Wait 7 days before rinsing or cleaning with a mild detergent.

CLEAN UP:

Clean all tools and equipment with clean water. For disposal of empty containers and unused product, contact your household refuse collection service.

*This information is provided "as is" and no representations or warranties, either expressed or implied, or merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information.





PREMIUM 2-PART EPOXY GARAGE FLOOR COATING GRAY & TAN KIT

NO. 950 & NO. 955

SURFACE PREPARATION:

New concrete must cure for a minimum of 30 days. For proper penetration and adhesion of topcoat, use BEHR® No. K-109924 Concrete Cleaner & Etcher (included in kit). Refer to product label for application instructions. Rinse surface well using a garden hose with the nozzle set in a stream pattern or pressure wash for best results. Allow the surface to dry completely. **IMPORTANT:** Excess residue may interfere with the adhesion of the BEHR® Premium 2-Part Epoxy Garage Floor Coating. Wipe your fingers over the clean floor to check for dust or powder. If either is visible on your fingers, repeat the rinsing step. Remove excess water with a squeegee or mop. Remove any remaining oil or grease spots on your concrete using BEHR® Concrete & Masonry Degreaser & Cleaner No. 990. Follow all label instructions.

WHERE NOT TO USE:

DO NOT apply on surfaces subject to hydrostatic pressure. All interior concrete floors are subject to possible moisture vapor rising from under the concrete, which may cause coating failure. Test for moisture by taping a 3' x 3' (1 x 1 m) piece of plastic directly to the concrete using duct tape on all edges. Allow the plastic to sit for 24 hours. If water droplets appear on the inside of the plastic after 24 hours or if the concrete is damp, the surface contains moisture and the floor should not be painted. Moisture problem must be corrected before coating. DO NOT apply over surfaces that have been treated with a concrete sealer or waterproofer. Test the surface by dripping a small amount of water onto the surface. If water beads and continues to stay on top, it indicates that a sealer is present and the BEHR® PREMIUM 2-PART EPOXY GARAGE FLOOR COATING may not adhere. The sealer must be removed before using this product. After stripping, re-test the surface for water absorbency. DO NOT use over loose or peeling previously painted surfaces. Test for loose, flaking paint by cutting an "X" in the paint with a single edge razor blade. Apply a piece of duct tape over the "X" and press firmly, then pull it off with an abrupt action. If the tape does not pull the paint from the surface, it can be coated. If the existing paint is removed, the loose paint should be removed down to a sound substrate using BEHR® Concrete & Masonry Paint Stripper No. 992. DO NOT use over loose or damaged concrete or if concrete dust is present. If the concrete is loose, chipping (spalled), or has concrete dust present, the coating will not adhere properly. Test for loose, flaking concrete by pressing a piece of masking or cellophane tape at various places, then pull it off with an abrupt action. If the tape does not pull the concrete from the surface, it can be coated. If the existing concrete is removed, the loose concrete must be removed down to a sound substrate. Loose or damaged concrete and cracks must be filled with a suitable concrete based patching material. Remove concrete dust using BEHR® Concrete & Masonry Degreaser & Cleaner No. 990. Follow all label instructions.

GENERAL INFORMATION:

IMPORTANT! DO NOT OPEN CAN WITHOUT READING INSTRUCTIONS. WARNING! This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm.

WARNING! IRRITANT! HARMFUL IF SWALLOWED. MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING OF VAPORS AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING.

USE WITH ADEQUATE VENTILATION. To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air. If properly used, a respirator (NIOSH approved for organic vapor with P series particulate pre-filter) may offer additional protection; obtain professional advice before using. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use. **FIRST AID:** If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately. **CAUTION: KEEP OUT OF REACH OF CHILDREN – DO NOT TAKE INTERNALLY.**

† **WARNING!** If you scrape sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.**

Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hot line at 1-800-424-LEAD or log on to www.epa.gov/lead. **WARNING!** This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm. **WARNING!** Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.