

3400 W. Segerstrom Avenue, Santa Ana, California 92704 or [www.behr.com](http://www.behr.com)



**BEHR®**  
**INT/EXT WET**  
**LOOK**  
**SEALER**  
**No. 985**

### **RECOMMENDED USES:**

*Use on previously coated or uncoated interior or exterior surface such as: Pavers, Concrete, Saltillo, and Unglazed Tiles, Brick, Aggregate, natural and Artificial Stone, Masonry and Stucco.*

**AVAILABLE IN:** Gallon & Five Gallon

### **COLORS**

No. 985 Clear Hi-Gloss\*

\*May not be available in all markets.

### **Tintable Bases/Max Tint**

\*NOT TINTABLE

### **FINISH**

Hi-Gloss.

\*Gloss Level 75.0-100.0 @ 60°

\*Substrate Dependant

### **COVERAGE RATE**

First Coat: 150-300 sq. ft. per gallon  
Second Coat: 300-400 sq. ft. per gallon. 4 mils wet, 1.2 mils dry

NOTE: Additional coats (no more than 4) may be added for a higher gloss and added protection. Spread rate is highly dependent on surface roughness and porosity. If sprayed, back-roll for uniform thickness.

### **DRYING TIME**

@77°F & 50% humidity\*

\*Longer dry time may be needed in cooler temperatures or in higher humidity.

To Touch: 1 Hours

Recoat: 4 Hours

Light Foot Traffic: 24 Hours

Repositioning Furniture: 72 Hours

Tire Traffic: Two Weeks

Cured: 30 Days

### **PRIMERS**

N/A

### **COMPOSITION**

**Vehicle/Active Ingredient:**

100% Acrylic

**Percent Solids By Volume:**

30%

**Percent Solids By Weight:**

32%

**Weight Per Gallon:**

8.5 lbs.

### **VOC**

35 gm/l Material (includes water)

97 gm/l Coating (excludes water)

### **Flashpoint**

N/A

### **MSDS**

Available @ [www.behr.com](http://www.behr.com)

Or 1-800-854-0133 Ext. 2

### **Clean Up**

Soap & Water. Recycle or dispose of paint call 1-800-CLEANUP (U.S.A. only) [www.earth911.org](http://www.earth911.org)

### **APPLICATION TOOLS**

**Airless Spray:** N/A

**Conventional Spray:** See manufacturer recommendations

**Pump Sprayer:** Adjustable Tip

**Brush:** Nylon/Polyester blend

**Roller:** 3/8"-1/2" Nap. Depending on the surface texture.

**Thinner:** Do Not Thin.

### **SURFACE PREPARATION**

New Concrete must cure for a minimum of 30 days. Remove dirt, oil and grease with BEHR® No. 990 Concrete Cleaner & Degreaser. Remove mildew or algae with BEHR No. 62 Multi-Surface Deck-Prep Cleaner & Mildew Stain Remover or bleach and water. For proper penetration and adhesion of topcoat on new or smooth concrete floors, use BEHR® No. 991 Concrete Etcher & Rust Remover. Rinse thoroughly (pressure wash for best results). Follow all label instructions.

### **APPLICATION**

Use product when surface and air temperature are between 50°-90°F. Intermix multiple containers, to ensure sheen uniformity. Apply using a high quality roller cover, nylon/polyester brush, or airless sprayer.

This information is believed to be reliable; however Behr Process Corporation makes no warranty, guarantee, or representation and assumes no liability as to the absolute correctness or sufficiency of the specifications.

**To Consult with a Technical Service Representative call 1-800-854-0133 Ext. 2**