



BELLAGIO FAUX

NO. 725 INTERIOR DECORATIVE FINISH

PRODUCT INFORMATION

BEHR PREMIUM PLUS® Interior Decorative Finish NO. 725 is a Bellagio faux designed for interior surfaces and offers a beautiful finish with a European fresco look. Creates depth and a unique washed look. Easy to apply and touch up. Durable washable finish. Apply over a flat enamel base color.

RECOMMENDED USES:

Use on previously painted or primed interior surfaces. Ideal for family rooms, living rooms, dining rooms, bedrooms, hallways and ceilings.



PRODUCT SPECIFICATIONS:

Tint Bases/Max Tint Load:

NO. 725 Untinted Base 128 oz / Do Not Tint

Sheen: Will vary depending on application technique

Vehicle Type: 100% Acrylic

***Weight per Gallon:** 9.3 lbs at +/- 2%

*% Solids:

By Volume: 22% at +/- 2%

By Weight: 28% at +/- 2%

VOC: <50 (g/l), meets the requirements for LEED credits, as the product meets VOC limits as established by Green Seal Standards GS-11, First Edition, May 20, 1993.

Flash Point: Not Applicable

***Coverage:** 250-350 SFPG, depending on application method and substrate porosity.

RECOMMENDED PRIMER / SYSTEMS:

PROPERLY PREPARED NEW SURFACES:

Gypsum Wallboard:

- BEHR PREMIUM PLUS® Interior No. 75 Enamel Undercoater primer & Sealer

Plaster:

- BEHR PREMIUM PLUS® Interior No. 75 Enamel Undercoater Primer & Sealer

Wood:

- BEHR PREMIUM PLUS® Interior/Exterior No. 434 Oil-Based Primer & Sealer
- BEHR PREMIUM PLUS® Interior No. 75 Enamel Undercoater Primer & Sealer

Tannin/Stainblocking:

- BEHR PREMIUM PLUS® Interior/Exterior No. 434 Oil-Based Primer & Sealer
- BEHR PREMIUM PLUS® Interior No. 75 Enamel Undercoater Primer & Sealer

Masonry:

- BEHR PREMIUM PLUS® Interior No. 75 Enamel Undercoater Primer & Sealer

Galvanized Metal, Metal & Aluminum:

- BEHR PREMIUM PLUS® Interior No. 75 Enamel Undercoater Primer & Sealer

PREVIOUSLY PAINTED SURFACES:

- BEHR PREMIUM PLUS® Interior/Exterior No. 434 Oil-Based Primer & Sealer
- BEHR PREMIUM PLUS® Interior No. 75 Enamel Undercoater Primer & Sealer

APPLICATION:

Note: Different applicators will provide different finishes and looks. Test product's application by making samples before beginning project.

Brush: Nylon/polyester, Whisk Broom, Sponge, Putty Knife or Trowel

Roller: Looped Roller, Short Nap Roller

Airless Spray: Not recommended

Tip: N/A

Filter: N/A

† **Dry Time:** @ 77° & 50% RH

Longer dry time may be required in cooler temperatures and higher humidity.

† To Touch: 15-20 Minutes

† To Recoat: 4 hours

† To Repaint: 24 - 48 Hours

† Full Cure: 1 week

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- Do not use on floors.
- For best results, apply at temperatures between 50°F - 90°F. Temperatures above 90°F may affect the application such as drying to fast. Avoid painting in direct sun. NOTE: If the surface is hot to the touch it should be considered to hot to apply this coating.
- Allow two weeks before washing or cleaning for full cure.
- Shelf life under normal conditions is two years unopened.

CLEAN UP:

Clean all tools and equipment with clean water. For disposal of empty containers and unused product, contact your household refuse collection service.

*This information is provided "as is" and no representations or warranties, either expressed or implied, or merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information.





BELLAGIO FAUX

NO. 725 INTERIOR DECORATIVE FINISH

† **WARNING!** If you scrape sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.**

Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. **WARNING!** This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm. **WARNING!** Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

SURFACE PREPARATION:

All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold and mildew stains, loose and peeling paint, rust and all other foreign substances.

Mildew: All surfaces must be clean of mold and mildew stains and dirt prior to coating.

Interior: Use one part BEHR® Premium Mildew Stain Remover No. 62 to three parts water (1:3 dilution).

DO NOT USE FULL STRENGTH. Avoid contact with clothing, carpet and fabrics. Apply using a clean cloth or sponge. Thoroughly rinse the surface with fresh water. Prolonged exposure on painted surfaces may damage finish.

New Drywall: All drywall surfaces should be sufficiently sanded smooth. Remove any remaining drywall dust prior to priming. Allow all drywall compounds to be completely dry prior to coating. **Previously Painted Gypsum Board/Drywall:** Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating. **Glossy Surfaces:** For maximum adhesion, sand the surface thoroughly before coating. **New Wood:** Remove mill glaze with sandpaper. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and

let dry completely. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Previously Painted Wood: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating. **Glossy Surfaces:** For maximum adhesion, sand the surface thoroughly before coating.

Wood: **WARNING!** Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

New Plaster: New plaster should be thoroughly dried out and cured for a minimum of 30 days before painting. When cured, clean using a mixed solution of one part vinegar and one part water to remove efflorescence and neutralize. **Previously Painted Plaster:** Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating. **Glossy Surfaces:** For maximum adhesion, sand the surface thoroughly before coating.

Stainblocking: After priming, test for stain bleed-through by applying the topcoat to a small section. If the stain bleeds through the topcoat, apply a second coat of primer and test again before top-coating the entire area. If bleeding continues, a longer dry time of the primer may be needed before top-coating.

Masonry: All masonry surfaces must be cured at least 30 days before painting. The pH must be 10.0 or lower prior to coating. Smooth masonry may require an adequate profile for adhesion. For all other smooth trowel concrete, create a profile using BEHR® Concrete & Masonry Surface Prep No. 991 or with mechanical means. Remove loose aggregate and debris using BEHR® Concrete & Masonry Cleaner/Degreaser No. 990. Scrub vigorously into the surface with a plastic brush, broom or power washer. **Rinse thoroughly with water and allow to dry**

*This information is provided "as is" and no representations or warranties, either expressed or implied, or merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information.

For MSDS or to consult with a BEHR® Certified Coatings Professional, call 1-800-854-0133 Ext. 2 (U.S.A. only). ©2010 BEHR PROCESS CORPORATION, Santa Ana, CA 92704 U.S.A.

Galvanized Metal, Metal & Alum
on new galvanized metal must be removed before



Revised 12/2010

it is painted. Remove oil film with a detergent and



**PREMIUM PLUS WITH STYLE
FAUX GLAZE**

NO. 748

PRODUCT INFORMATION

This unique, water-based translucent product is designed for blending with BEHR PREMIUM PLUS ULTRA® or BEHR PREMIUM PLUS® Interior paints and applied using decorative paint applicators. This mixture extends the paint's open time allowing you to create dynamic faux-painted finishes and unique decorative wall designs.

RECOMMENDED USES:

Properly painted interior surfaces. Ideal for types of living and working spaces such as; Family Rooms, Living Rooms, Dining Rooms, Bedrooms, Kids' Rooms, Hallways, Kitchens, Bathrooms, Doors, Trim, Ceilings and offices.

PRODUCT SPECIFICATIONS:

Tint Bases/Max Tint Load:

No. 748 Faux Glaze 128 oz

Sheen/Gloss: Not Applicable

Vehicle Type: Acrylic

***Weight Per Gallon:** 8.8 +/- 0.2 lbs./gal

***% Solids:**

By Volume: 20.5 +/- 2%

By Weight: 24.2 +/- 2%

VOC: <350 (g/l)

Flash Point: Not Applicable

Viscosity: 85-95 KU (un-tinted)

Recommended Film Thickness:

Wet: 4.0 Dry: 0.8 mils @ 400 SFPG

Coverage: Typical coverage is 400 sq. ft (37 m2) per gallon. Coverage may vary depending upon the surface and the desired effect.

Application:

Brush: Nylon/polyester

Roller: Use 3/8"-1/2" nap cover on smooth surfaces and 1/2"-3/4" on rough, porous surfaces.

Thinning: (If required) No more than 1/2 pint of water per gallon.

APPLICATION:

Remove loose paint, wash off any dirt and grease with detergent and remove mildew stains with BEHR® PREMIUM MOLD & MILDEW STAIN REMOVER NO. 62. Rinse and allow to dry. Scuff sand glossy surfaces. Countersink nailheads, repair imperfections and sand smooth. Remove all dust with a damp cloth and allow to dry. Allow new stucco, plaster and masonry to cure 30 days before priming. Use BEHR® ENAMEL UNDERCOATER PRIMER & SEALER NO. 75. Apply Interior Eggshell, Satin or Semi-Gloss sheen for the base color according to label instructions.

In a plastic container, blend 1 part paint (1 quart) to 4 parts glaze (1 gallon) for each selected glaze color. Stir glaze mixture until thoroughly blended and occasionally during application. Refer to the BEHR Faux Glazing Colors & Techniques Guide and www.behr.com for additional instructions on application. Using the appropriate tool and technique, apply the glaze color over the dried base color. Work in 3' x 3' (90 x 90 cm) areas or smaller depending on the technique. Blend from section to section in a random pattern and maintain a wet edge to ensure smooth transitions.

APPLICATION TOOLS:

Brush: Nylon/polyester

Roller: Use 3/8 nap cover

Air-less Spray: At packaged consistency

Tip: .015"

Filter: 60 mesh

Thinning: Do not thin



DRY TIME:

- 75°F (24°C) and 50% RH
- Dries to Touch 1 hour
- 4 hours before recoating

CLEAN UP:

Brushes and other equipment can be cleaned with warm, soapy water. For disposal of empty containers and unused product, contact your household refuse collection service.

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- For best results, apply at temperatures between 50°F - 90°F. Temperatures above 90°F may affect the application such as drying too fast. Avoid painting in direct sun. NOTE: If the surface is hot to the touch it should be considered too hot to apply this coating.
- Avoid heavy traffic for 24 hours.
- Allow two weeks before washing or cleaning for full cure.
- Shelf life under normal conditions is two years unopened.

IMPORTANT! DO NOT OPEN CAN WITHOUT READING THESE INSTRUCTIONS.

This water-based translucent product is to be blended with BEHR PREMIUM PLUS® Interior paints. The paint and glaze mixture extends the paint's open time to allow you to create unique decorative wall designs.

*This information is provided "as is" and no representations or warranties, either expressed or implied, or merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information.





PREMIUM PLUS WITH STYLE FAUX GLAZE

NO. 748

SURFACE PREPARATION:

New Drywall: All drywall surfaces should be sufficiently sanded smooth. Remove any remaining drywall dust prior to priming. Allow all drywall compounds to be completely dry prior to coating.

Previously Painted Gypsum Board/Drywall: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, sand the surface thoroughly before coating.

New Plaster: New plaster should be thoroughly dried out and cured for a minimum of 30 days before painting. When cured, clean using a mixed solution of one part vinegar and one part water to remove efflorescence and neutralize.

Previously Painted Plaster: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, sand the surface thoroughly before coating.

GENERAL INFORMATION:

IMPORTANT! DO NOT OPEN CAN WITHOUT READING INSTRUCTIONS. WARNING! This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm.

WARNING! IRRITANT! HARMFUL IF SWALLOWED. CONTAINS: ETHYLENE GLYCOL. MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING OF VAPORS AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING.

USE ONLY WITH ADEQUATE VENTILATION. To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air. If properly used, a respirator (NIOSH approved for organic vapor with P series particulate pre-filter) may offer additional protection; obtain professional advice before using. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use.

FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CAUTION: KEEP OUT OF REACH OF CHILDREN – DO NOT TAKE INTERNALLY.

† WARNING! If you scrape sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hot line at 1-800-424-LEAD or log on to www.epa.gov/lead. **WARNING!** This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm. **WARNING!** Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.





**PREMIUM PLUS WITH STYLE
VENETIAN PLASTER**

NO. 770

PRODUCT INFORMATION

Behr® Venetian Plaster is a heavy-bodied decorative paste like plaster finish for interior applications such as on ceilings and walls, providing a decorative, elegant, glossy finish when burnished. This decorative finish has origins dating as far back as Ancient Greece. This sophisticated look of polished marble provides a smooth finish for all types of living spaces and the more layers that are applied the more depth and polished finish can be achieved.

RECOMMENDED USES:

On properly prepared interior surfaces and ideal for walls and ceilings such as: Living Rooms, Dining Rooms, Bedrooms, Offices, and Hotels when a premium decorative finish is desired. Apply 2 coats on smooth surfaces. In high moisture or high traffic areas, apply BEHR VENETIAN PLASTER TOPCOAT NO. 775 over the VENETIAN PLASTER finish without burnishing. Topcoat dries to a satin sheen.

PRODUCT SPECIFICATIONS:

Tint Bases/Max Tint Load: No. 770 120 oz. / 10 oz.

Sheen/Gloss:

- 1-1.5 @ 20°
- 2.0-2.5 @ 60°
- 1-2 @ 85°

Vehicle Type: Vinyl Acetate

***Weight Per Gallon:** 13.2 +/- 0.2 lbs./gal

***% Solids:**

- By Volume: 43.9 +/- 2%
- By Weight: 64.4 +/- 2%

VOC: <100 (g/l)

Flash Point: Not Applicable

Viscosity: 120-125 KU

Recommended Film Thickness:

N/A – Can vary depending on the desired finish.

Coverage: Typical coverage is 150 sq. ft. (14 m2) per gallon with 2 coat application.

Application:

Tool: Flexible steel trowel or drywall trowel

Thinning: DO NOT THIN

APPLICATION:

Refer to the BEHR Faux Textures Colors & Techniques Guide and www.behr.com for additional instructions on application. Use product on smooth surfaces when the surface and air temperatures are between 50-90°F (10-32°C). DO NOT THIN. FIRST COAT: Apply product using a straight edged flexible steel trowel or wall scraper. Hold trowel at a 15°-30° angle, spreading a thin layer of the product across the surface. Complete coverage is not necessary. Allow to dry approximately 4 hours. SECOND COAT: Hold trowel at a 60°-90° angle to the surface, spreading a thin layer of the product, filling in the empty areas.

After the second coat has dried at least 24 hours, a polished effect can be created by sanding the surface with 400 or 600 grit sandpaper, removing the plaster dust and then rubbing the surface with the flat side of the steel trowel. In high moisture or high traffic areas, apply BEHR VENETIAN PLASTER TOPCOAT NO. 775 over the VENETIAN PLASTER finish without burnishing. Topcoat dries to a satin sheen.

After the second coat has dried at least 24 hours, a polished effect can be created by sanding the surface with 400 or 600 grit sandpaper, removing the plaster dust and then rubbing the surface with the flat side of the steel trowel. In high moisture or high traffic areas, apply BEHR VENETIAN PLASTER TOPCOAT NO. 775 over the VENETIAN PLASTER finish without burnishing. Topcoat dries to a satin sheen.

DRY TIME:

- 75°F (24°C) and 50% RH

Allow first coat to dry 4 hours. If burnishing, allow second coat to dry at least 24 hours and burnish within 7 days of application. Longer dry time required in cooler temperatures and in higher humidity.



CLEAN UP:

Brushes and other equipment can be cleaned with warm, soapy water. For disposal of empty containers and unused product, contact your household refuse collection service.

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- For best results, apply at temperatures between 50°F - 90°F. Temperatures above 90°F may affect the application such as drying to fast. Avoid painting in direct sun. NOTE: If the surface is hot to the touch it should be considered to hot to apply this coating.
- Avoid heavy traffic for 24 hours.
- Allow two weeks before washing or cleaning for full cure.

*This information is provided "as is" and no representations or warranties, either expressed or implied, or merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information.





PREMIUM PLUS WITH STYLE VENETIAN PLASTER

NO. 770

- Shelf life under normal conditions is two years unopened.

SURFACE PREPARATION:

New Drywall: All drywall surfaces should be sufficiently sanded smooth. Remove any remaining drywall dust prior to priming. Allow all drywall compounds to be completely dry prior to coating.

Previously Painted Gypsum Board/Drywall: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, silicized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, sand the surface thoroughly before coating.

New Plaster: New plaster should be thoroughly dried out and cured for a minimum of 30 days before painting. When cured, clean using a mixed solution of one part vinegar and one part water to remove efflorescence and neutralize.

Previously Painted Plaster: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, silicized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, sand the surface thoroughly before coating.

GENERAL INFORMATION:

IMPORTANT! DO NOT OPEN CAN WITHOUT READING INSTRUCTIONS. WARNING! This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm.

WARNING! IRRITANT! HARMFUL IF SWALLOWED. CONTAINS: ETHYLENE GLYCOL. MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING OF VAPORS AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING.

USE ONLY WITH ADEQUATE VENTILATION. To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air. If properly used, a respirator (NIOSH approved for organic vapor with P series particulate pre-filter) may offer additional protection; obtain professional advice before using. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use.

FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15-20 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CAUTION: KEEP OUT OF REACH OF CHILDREN – DO NOT TAKE INTERNALLY.



**PREMIUM PLUS WITH STYLE
VENETIAN PLASTER TOP COAT**

NO. 775

PRODUCT INFORMATION

This 100% Acrylic, water-based, clear protective finish increases the durability and sheen of BEHR VENETIAN PLASTER.

RECOMMENDED USES:

Apply after the VENETIAN PLASTER finish has completely dried at approximately 24 hours. Do not burnish the surface before or after the application of the VENETIAN PLASTER TOPCOAT.



PRODUCT SPECIFICATIONS:

Base: No. 775.

Sheen/Gloss:

- 1.5-2.0 @ 20°
- 10-15 @ 60°
- 15-20 @ 85°

Vehicle Type: 100% Acrylic

***Weight Per Gallon:** 8.5 +/- 0.2 lbs./gal

% Solids:

- By Volume: 23.2 +/- 2%
- By Weight: 29.2 +/- 2%

VOC: <275 (g/l)

Flash Point: Not Applicable

Viscosity: 120-130 KU

Recommended Film Thickness:

N/A – Can vary depending on the desired finish.

Coverage: Typical spread rate is 200

sq. ft. (19 m²) per quart.

Application:

Tool: Flexible steel trowel or drywall trowel

Thinning: DO NOT THIN

APPLICATION:

Refer to the BEHR Faux Textures Colors & Techniques Guide and www.behr.com for additional instructions on application. DO NOT THIN. Stir occasionally. Use product when the surface and air temperatures are between 50°-90°F (10°-32°C). Apply using a straight-edged, flexible steel trowel or wall scraper. Hold trowel at an angle and spread a very thin, even coat of the product across the surface. Remove any excess topcoat with a damp rag or sponge. The topcoat will dry to a Satin sheen and darken the tone and/or color of the finish.

DRY TIME:

- 75°F (24°C) and 50% RH
- Dries to Touch 1 hour
- Cure: 24 hours

CLEAN UP:

Brushes and other equipment can be cleaned with warm, soapy water. For disposal of empty containers and unused product, contact your household refuse collection service.

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- For best results, apply at temperatures between 50°F - 90°F. Temperatures above 90°F may affect the application such as drying to fast. Avoid painting in direct sun. NOTE: If the surface is hot to the touch it should be considered to hot to apply this coating.
- Avoid heavy traffic for 24 hours.
- Allow two weeks before washing or cleaning for full cure.
- Shelf life under normal conditions is two years unopened.

SURFACE PREPARATION:

New Drywall: All drywall surfaces should be sufficiently sanded smooth. Remove any remaining drywall dust prior to priming. Allow all drywall compounds to be completely dry prior to coating.

Previously Painted Gypsum Board/Drywall: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, sand the surface thoroughly before coating.

New Plaster: New plaster should be thoroughly dried out and cured for a minimum of 30 days before painting. When cured, clean using a mixed solution of one part vinegar and one part water to remove efflorescence and neutralize.

Previously Painted Plaster: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, sand the surface thoroughly before coating.

*This information is provided "as is" and no representations or warranties, either expressed or implied, or merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information.

For MSDS or to consult with a BEHR® Certified Coatings Professional, call 1-800-854-0133 Ext. 2 (U.S.A. only). ©2009 BEHR PROCESS CORPORATION Santa Ana, CA 92704 U.S.A.





PREMIUM PLUS WITH STYLE VENETIAN PLASTER TOP COAT

NO. 775

GENERAL INFORMATION:

IMPORTANT! DO NOT OPEN CAN WITHOUT READING INSTRUCTIONS. WARNING! This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm.

WARNING! IRRITANT! HARMFUL IF SWALLOWED. CONTAINS: ETHYLENE GLYCOL. MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING OF VAPORS AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING.

USE ONLY WITH ADEQUATE VENTILATION. To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air. If properly used, a respirator (NIOSH approved for organic vapor with P series particulate pre-filter) may offer additional protection; obtain professional advice before using. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use.

FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CAUTION: KEEP OUT OF REACH OF CHILDREN – DO NOT TAKE INTERNALLY.

† **WARNING!** If you scrape sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hot line at 1-800-424-LEAD or log on to www.epa.gov/lead. **WARNING!** This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm. **WARNING!** Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.